


OMNISPORTS PUREPLAY

TECHNICAL DATA

Description

Heterogeneous indoor floorcovering, 9.4mm thick.

- (1) Engineered surface embossing
- (2) Top Clean XP treatment
- (3) Pure transparent vinyl wear layer
- (4) High definition printing
- (5) Unwoven glas fiber
- (6) Homogeneous calendered sheet - recycled vinyl
- (7) High-density closed cell foam



PROPERTIES	STANDARDS	OMNISPORTS PUREPLAY
DoP n°		
0120-071-DoP-2016-04		
CLASSIFICATION		
Type of floor covering	EN 14904	Heterogeneous indoor floorcoverings
TECHNICAL CHARACTERISTICS		
Total thickness	ISO 24346 (EN 428)	9.4mm
Total weight	ISO 23997 (EN 430)	6200g/m ²
Width	ISO 24341 (EN 426)	2m
Length	ISO 24341 (EN 426)	20.5lm
REQUIREMENTS FOR SAFE USE		
Friction	EN 13036-4	80 to 110
Shock absorption	EN 14808	P2 ≥35%
Vertical deformation	EN 14809	P2
Specular gloss	EN ISO 2813	≤30
TECHNICAL PERFORMANCES		
Vertical ball behaviour	EN 12235	≥90%
Reaction to fire	EN 13501-1	Cfl-s1*
Resistance to wear	EN ISO 5470-1	≤1g
Resistance to indentation	Average measured value EN 1516	Compliant ≤0.50mm
Resistance to a rolling load	EN 1569	≤0.50mm
In room noise	NFS-074	Class A ≤65dB
Thermal resistance	EN ISO 14456	Approx. 0.14 m ² K/W

* glued and GreenLay installation on concrete
Installation and maintenance guides available on request

Technical data in force as from the date of publication (06/2020).

The values above correspond to laboratory test (no in situ test), and are subject to modifications for the benefit of further improvement.

For more detailed technical information, please contact Tarkett.

Colors of the products shown in the photos or samples are indicative only. There may be differences in color, gloss and embossing structure between the products sold and photos or samples.



TarkettSPORTS